

Classifications

EN ISO 14343-A	AWS A5.9 / SFA-5.9
W 20 25 5 Cu L	ER385

Characteristics and typical fields of application

TIG rod of W 20 25 5 Cu L / ER385 for joining and surfacing work on matching austenitic 1.4539 / 904L CrNiMoCu-steels and cast steel grades. For joining these steels with unalloyed / low-alloy steels and cast steel grades. Good corrosion resistance similar to matching steels and cast steel grades, above all in reducing environment. Max. service temperature 350°C.

Base materials

1.4465 X1CrNiMoN25-25-2, 1.4505 X4NiCrMoCuNb20-18-2, 1.4506 X5NiCrMoCuTi20-18, 1.4537 X1CrNiMoCuN25-25-5, 1.4538 X2NiCrMoCuN20-18, 1.4539 X2NiCrMoCuN25-20-5, 1.4586 X5NiCrMoCuNb22-18
UNS N08904, S31726
AISI 904L

Typical analysis

	C	Si	Mn	Cr	Ni	Mo	Cu
wt.-%	< 0.025	0.2	2.5	20.5	25.0	4.8	1.5

Mechanical properties of all-weld metal - typical values (min. values)

Condition	Yield strength $R_{p0.2}$	Tensile strength R_m	Elongation A ($L_0=5d_0$)	Impact energy ISO-V KV J
	MPa	MPa	%	20°C
u	350	550	35	120

u untreated, as-welded – shielding gas Ar

Operating data

	Polarity	DC-	Dimension mm
	Shielding gas (EN ISO 14175)	I1	1.6 × 1000
	Rod marking	+ W 20 25 5 Cu L / ER385	2.0 × 1000
			2.4 × 1000
			3.2 × 1000

Heat input max.1.5 kJ/mm, interpass temperature max. 150°C.

No preheating unless required by the parent material.

Post-weld heat treatment generally not needed. In special cases, solution annealing can be performed at 1120°C followed by water quenching.

Approvals

TÜV (04301), CE